


gipkoll

Cementitious adhesive
for absorbent coatings

grigio

 **UNI EN 12004**
C1TE



ADHESIVES AND JOINTS



Gipkoll Grigio

Cementitious adhesive for absorbent coatings




TECHNICAL FEATURES

Complies with UNI EN 12004 - C1TE

Theoretical yield	~ 5÷7 Kg/m ²
Apparent specific weight	~ 1340 Kg/m ³
Granulometry	≤ 0,6 mm
Mixing water	28%
Execution of joints	after 48 h
Open time	20 min
Flexibility	Limited
Reaction to fire	A1 Class
Adhesion by traction 28 days AF-T	≥ 0,7 N/mm ²
Adhesion after heat action AF-T CF-A	≥ 0,6 N/mm ²
Adhesion after immersion AF-T CF-A	≥ 0,6 N/mm ²
Adhesion after freeze/thaw cycles CF-A	≥ 0,6 N/mm ²
Vertical slip	≥ 0,5 N/mm ²

Laboratory tests performed at + 20 ° C and R.H. 65%, data subject to variations in different atmospheric and installation conditions.



METHOD OF USE

Mix and blend the product only with clean water (≈ 22%) to obtain a mixture free of lumps (pasty consistency). Leave the mixture to stand for about 5 minutes then remix and apply. Spread the mixture with the special toothed spatula onto a clean substrate and on surface finishes (spreading twice). Apply the tiles and beat them carefully to improve adhesion. Fill joints at least 48 hours after laying the flooring.



WARNINGS

Do not add additives or aggregates of any kind.
Do not apply on inconsistent, dusty or degraded, frozen or wet substrates.
Do not apply at temperatures below + 5 ° C or above + 35 ° C.
Do not apply in conditions of intense sun, high wind or possible rain.
Keep the product in the bags intact, on pallets and in a dry and ventilated place.



PACKAGING

Paper bags of kg. 25. Color: grey.

The above information is to be considered indicative, non-binding and subject to change without notice.
Therefore the suitability of the product for the desired result must be verified by the user, who is fully responsible for its use.