

# *rasostuck*

Powder stucco  
for interior rendering



**GYPSUM-BASED | RENDERS**



# Rasostuck

Powder stucco for interior rendering

## TECHNICAL FEATURES



<b>Theoretical yield</b>	~ 1 Kg/m <sup>2</sup> for 1 mm thick
<b>Apparent specific weight</b>	700 Kg/m <sup>3</sup>
<b>Granulometry</b>	≤ 0,100 mm
<b>Mixing water</b>	~ 60 %
<b>Setting Time</b>	100 min. ± 20 min.
<b>Resistance to fire</b>	A1 Class
<b>Compressive strength</b>	≥ 2 N/mm <sup>2</sup>

Laboratory tests performed at + 20 ° C and R.H. 65%, data subject to variations in different atmospheric and installation conditions.



### METHOD OF USE

Mix and blend the product only with clean water (≈ 55%) to obtain a mixture free of lumps (pasty consistency). Spread the mixture using suitable tools appropriate for the job. If filling joints, apply the mesh between the first and second coats, inserting it between the two layers. **Setting time: 90 '.**



### WARNINGS

Do not add additives or aggregates of any kind.  
Do not apply on inconsistent, dusty or degraded, frozen or wet substrates.  
Do not apply at temperatures below + 5 ° C or above + 35 ° C.  
Do not apply in conditions of intense sun, high wind or possible rain.  
Keep the product in the bags intact, on pallets and in a dry and ventilated place.



### PACKAGING

Paper bags of 15, kg 4 e kg 1.

The above information is to be considered indicative, non-binding and subject to change without notice.  
Therefore the suitability of the product for the desired result must be verified by the user, who is fully responsible for its use.