

scagliola

Ready mixed hemihydrate
gypsum undercoat for interiors



GYPSUM-BASED | RENDERS



Scagliola

Ready mixed hemihydrate gypsum undercoat for interiors



TECHNICAL FEATURES

Compliant with UNI EN 13279 - B1/20/2 class 1



Theoretical yield (plaster)	~ 9 Kg/m ² for 1 cm thick
Theoretical yield (finishing)	~ 1,5 Kg/m ² for 1 cm thick
Apparent specific weight	~ 640 Kg/m ³ (free-fall)
Mixing water	72÷75% (~18 lt/bags of 25 Kg)
Reaction to fire	A1 class
Compressive strength	~ 4,8 N/mm ²
Adhesion to the support	≥ 0,16 N/mm ²

Laboratory tests performed at + 20°C and R.H. 65%, data subject to variations in different atmospheric and installation conditions.



METHOD OF USE

Sprinkle the product uniformly into a container of clean water until complete absorption, leave to rest to avoid the formation of lumps, then remix only the part of the product to be used.



WARNINGS

Do not add additives or aggregates of any kind.
Do not apply on inconsistent, dusty or degraded, frozen or wet substrates.
Do not apply at temperatures below + 5 ° C or above + 35 ° C.
Do not apply on wooden or metal substrates not previously treated with Primer Gps.
Keep the product in the bags intact, on pallets and in a dry and ventilated place.



PACKAGING

Paper bags of kg. 25.

The above information is to be considered indicative, non-binding and subject to change without notice.
Therefore the suitability of the product for the desired result must be verified by the user, who is fully responsible for its use.