



**GYPSUM-BASED | RENDERS** 

# **Intofin Plus**

Ready mixed product for smooth interior finishing



#### **TECHNICAL FEATURES**

Compliant with UNI EN 13279 - C7/20/2 class 1

Theoretical yield	~ 1 Kg/m² for 1 mm thick
Specific weight applied dry	~ 1000 Kg/m³
Mixing water	0,6 lt/kg
Start taking	100 min. ± 20 min.
End taking	115 min. ± 30 min.
Permeability to vapor	μ=6
Resistance to fire	A1 class
Compressive strength	2,0 N/mm²

Laboratory tests performed at + 20  $^\circ$  C and R.H. 65%, data subject to variations in different atmospheric and installation conditions.



# METHOD OF USE

Mix with water using a trowel or low speed drill to achieve a smooth mixture free of lumps and taking care to mix only the amount of product required for use within 1 hour of mixing. Scrape off the surface and fill cracks with Intofin Plus one hour before rendering. The mixture can be applied with a trowel or spatula in two coats, in double strokes at right angles, on a wall or ceiling background plaster, well cleaned with a scraper or metal edge, free of holes or irregularities and cured for at least 24 hours. A final application by spatula of two coats of a final thin layer of mixture improves the fineness and gloss of the finish. Avoid any additions (aggregates, binders, various additives) to the premixed product and applications of thicknesses > 3mm.



## WARNINGS

Do not add additives or aggregates of any kind. Do not apply on inconsistent, dusty or degraded, frozen or wet substrates. Do not apply at temperatures below + 5 ° C or above + 35 ° C. Do not apply in conditions of intense sun, high wind or possible rain. Keep the product in the bags intact, on pallets and in a dry and ventilated place.



## PACKAGING

Paper bags of kg. 25.

The above information is to be considered indicative, non-binding and subject to change without notice. Therefore the suitability of the product for the desired result must be verified by the user, who is fully responsible for its use.