


# *tonacem*

## *grigio*

Ready mixed plaster  
based on cement and  
hydrated lime for finishing  
civil plastering



CEMENT-BASED | PLASTERS



# Tonacem Grigio

Ready mixed plaster based on cement and hydrated lime for finishing civil plastering




## TECHNICAL FEATURES

Compliant with UNI EN 998 - 1



<b>Theoretical yield</b>	~ 1,0-1,2 Kg/m <sup>2</sup> for 1 mm thick
<b>Apparent specific weight</b>	~ 1000 Kg/m <sup>3</sup>
<b>Granulometry</b>	≤ 0,7 mm
<b>Mixing water</b>	~ 35%
<b>Start taking</b>	~ 180 min.
<b>Mixture life time</b>	~ 120 min.
<b>Permeability to water vapor (EN 1015-19)</b>	μ < 15
<b>Thermal conductivity (λ<sub>10, dry</sub>) (EN 1745)</b>	λ = 0,43 W/mK (tabulated value P=50%)
<b>Reaction to fire</b>	A1 class
<b>Recommended application thickness</b>	3-5 mm
<b>Adhesion to the support</b>	≥0,2 N/mm <sup>2</sup>

Laboratory tests performed at + 20°C and R.H. 65%, data subject to variations in different atmospheric and installation conditions.



## METHOD OF USE

GIPSOS primer. The product is mixed with clean water using a low speed whisk mixer to obtain a smooth mixture free of lumps. Wait 5 minutes, remix and then apply with a metal trowel to a thickness of about 2 mm per coat up to a maximum depth of 10 mm. After about 30 minutes use a damp sponge trowel to smooth the surface for a "civil grade" smooth finish. After curing the product can be covered with synthetic plaster or paint.



## WARNINGS

Do not add additives or aggregates of any kind.  
Do not apply on inconsistent, dusty or degraded, frozen or wet substrates.  
Do not apply at temperatures below + 5 ° C or above + 35 ° C.  
Do not apply in conditions of intense sun, high wind or possible rain.  
Keep the product in the bags intact, on pallets and in a dry and ventilated place.



## PACKAGING

Paper bags of kg. 25. Colour: Grey

The above information is to be considered indicative, non-binding and subject to change without notice.  
Therefore the suitability of the product for the desired result must be verified by the user, who is fully responsible for its use.