


palladio

SILOXANE COATING

Siloxane mineral coating based on stabilised mineral colloids, indicated as finishing of new buildings and in the restoration of historic buildings or at the seaside.


Grain from 0.6 to 1.6.

Application



by spatula

Finishing



plastic trowel

Palladio

Siloxane coating



TECHNICAL FEATURES

Expected yield	~ 2,50 Kg/m ²
Viscosity	~ 140.000 mPa*s
Specific weight	~ 1,80 Kg\Lt
PH	> 9,00
Colours	Folder colors
Classification by final use	Decoration and Protection

CHARACTERISTICS OF INSTALLATION

Outside rain	after 8 hours
Dry to the touch	~ 10 hours
Deep dry	~ 36-48 hours

Laboratory tests performed at + 20 ° C and R.H. 65%, data subject to variations in different atmospheric and installation conditions.



METHOD OF USE

The walls should be mature and dry, free from dust and dirt. Brush and dust any loose parts, oily residues, plant formations, saline efflorescence or processing residues. Treat in advance with PALLADIUM PRIMER SILOSSANICO surfaces that are particularly absorbent or have strong differences in absorption and plasters that are not very consistent and flaky. In the case of non-friable plasters or consistent smoothing it is sufficient to insulate with a layer of PALLADIUM SILOXANE PAINTING. The application is done by laying with steel trowel and subsequent finishing with plastic trowel in one hand.



WARNINGS

*The chromatic aspect may vary according to the absorption of the support and the climatic conditions.
Do not apply on inconsistent, dusty or degraded, frozen or wet substrates.
Do not apply at temperatures below + 5 ° C or above + 35 ° C.
Do not apply in conditions of intense sun, high wind or possible rain.
Keep the product in the bags intact, on pallets and in a dry and ventilated place.*



PACKAGING

Plastic tanks of kg. 25

*The above information is to be considered indicative, non-binding and subject to change without notice.
Therefore the suitability of the product for the desired result must be verified by the user, who is fully responsible for its use.*