

Breathable paint for indoor use of opaque appearance, indicated for the painting of internal walls such as cellars, garages, closets, stairwells, sheds etc.

Application



by brush



by roller



by spray



Michelangelo

Idropittura a tempera



TECHNICAL FEATURES

Expected yield	~ 0,200 Lt/m² two-hand
Viscosity	~ 45.000 mPa*s
Specific weight	~ 1,70 Kg\Lt
РН	> 9,00
Covering power	96 < Valore Tristimolo Y < 98
Water absorption	W < 0,5 Kg/(m ² xH ^{0,5})
Classification by final use	Decoration and Protection

CHARACTERISTICS OF INSTALLATION

First hand dilution with water	40%
Second hand dilution with water	30%
Interval between 1st and 2nd hand	about 10 hours
Dry to the touch	~ 1 hour
Deep dry	~ 48 hours

Laboratory tests performed at +20 ° C and R.H. 65%, data subject to variations in different atmospheric and installation conditions.



METHOD OF USE

The walls should be mature and dry, free of dust and dirt. Brush and dust any loose parts, oily residues, plant formations, saline efflorescence or processing residues. Deal with BRUNELLESCHI ACRYLIC PRIMER in advance particularly absorbent surfaces or with strong differences in absorption and poorly consistent and shaky plasters. Can be applied with brush, roller or spray. The first coat should be diluted with 30% water, the second with 20%.



WARNINGS

The chromatic aspect may vary according to the absorption of the support and the climatic conditions.

Do not apply on inconsistent, dusty or degraded, frozen or wet substrates.

Do not apply at temperatures below + 5 ° C or above + 35 ° C.

Do not apply in conditions of intense sun, high wind or possible rain.

Keep the product in the bags intact, on pallets and in a dry and ventilated place.



WARNINGS

Plastic tanks of Lt. 14

The above information is to be considered indicative, non-binding and subject to change without notice.

Therefore the suitability of the product for the desired result must be verified by the user, who is fully responsible for its use.