

# gessokoll

Ready mixed adhesive  
based on hemihdrate gypsum,  
limestone fillers and additives.

 **UNI EN 12860**



GYPSUM-BASED | ADHESIVE



# CESSOKOLL

Ready mixed adhesive based on hemihydrate gypsum, limestone fillers and additives, for interiors.



## TECHNICAL FEATURES

Compliant with UNI EN 12860

<b>Theoretical yield</b>	~ 4,5 Kg/m <sup>2</sup> per 1 mm di spessore
<b>Theoretical yield (bonding)</b>	~ 3-5 Kg/m <sup>2</sup>
<b>Apparent specific weight</b>	~ 700 Kg/m <sup>3</sup>
<b>Granulometry</b>	< 2 mm
<b>Mixing water</b>	60/70% (~18 lt/sacco da 25 Kg)
<b>Start taking</b>	~ 80/120 min
<b>Reaction to fire</b>	Classe A1
<b>Tear resistance</b>	≥ 1 N/mm <sup>2</sup>

Laboratory tests performed at + 20°C e R.H. 65%, data subject to variationis in different atmospheric and installation conditions.



## METHOD OF USE

**Gessokoll is suitable for the assembly of plasterboard sheets, plaster blocks, fibre-reinforced plaster, plaster ornaments etc...**

Mix and knead the product with clean water only (~ 60/70%) until a lump-free mixture is obtained (pasty consistency). Let the mixture rest for about 5 minutes, then mix again before applying. Spread the mixture with a special toothed spatula on the well-cleaned support and on the covering (double spreading).



## WARNINGS

Do not add additives or inert materials of any kind.  
Do not apply on inconsistent, dusty or degraded, frozen or wet surfaces.  
Do not apply at temperatures below +5°C or above +35°C.  
Keep the product in intact bags, on pallets and in a dry and ventilated place.



## PACKAGING

Paper bag of kg. 25. On pallets of 30/60 paper bags.

*The information above is to be considered indicative, not binding and subject to change without notice. Therefore, the suitability of the product for the desired result must be verified by the user, who is to be considered fully responsible for its use.*